

Table 5.1; ARC THM 98: Context and identification of assessed slag

Context	Sample	Identification	Weight g	Length	Width	Depth	Comments
10276	10276	undiagnostic	522				
10510		smithing hearth bottom	424	95	70	50	
10510		undiagnostic	110				
10528		smithing hearth bottom	2218	140	130	90	poss. not Roman?
10657		smithing hearth bottom	214	80	60	25	
10657		undiagnostic	70				
10788		undiagnostic	14				
10832		fayalitic run	4				
10832		vitriified hearth lining	92				
10935		undiagnostic	114				not ironworking?
10968		undiagnostic	18				
10968		undiagnostic	230				poss. smelting
11303		undiagnostic	54				
11318		smithing hearth bottom	318	70	70	40	
11336		undiagnostic	32				
11392		undiagnostic	74				not ironworking?
11405		undiagnostic	120				
11451		cinder	98				
11468		undiagnostic	180				
11475		smithing hearth bottom	292	80	65	40	
11564		smithing hearth bottom	262	80	75	30	
11564		undiagnostic	98				
11652		smithing hearth bottom	292	80	75	30	
11652		undiagnostic	42				
11961		tap slag	248				
11961		undiagnostic	18				
12066		smithing hearth bottom	440	110	80	25	
12279		undiagnostic	170				
12291		undiagnostic	182				
12320		smithing hearth bottom	306	90	70	40	
12378		smithing hearth bottom	210	70	60	30	
12378		undiagnostic	250				
12434		smithing hearth bottom	190	60	55	40	
15062		smithing hearth bottom	128	80	70	20	
15177		smithing hearth bottom	198	75	65	35	
15178		smithing hearth bottom	94	65	55	25	
15179		smithing hearth bottom	150	65	55	25	
15179		undiagnostic	188				
20045		vitriified hearth lining	110				mixed with undiagnostic
20056	10090	flake	0				
20056		hammerscale in soil	0				
20056		undiagnostic	886				
20056		vitriified hearth lining	410				
20058	10070	some broken flake	0				
20058	10072	flake and some spheres	0				
20058	10075	broken flake	0				
20058	10076	broken flake	0				
20058	10078	some broken flake	0				
20058	10079	a little flake	0				
20058	10082	some broken flake	0				
20058	10088	no hammerscale	0				
20058		smithing hearth bottom	80	75	45	25	
20058		smithing hearth bottom	126	90	50	30	
20058		smithing hearth bottom	174	75	60	30	
20058		undiagnostic	1730				

Context	Sample	Identification	Weight g	Length	Width	Depth	Comments
20058		vitriified hearth lining	364				
20074	10174	magnetic pebbles?	0				
20074	10187	very, very little	0				
20074	10191	very little hammerscale	0				
20074	10229	a little flake	0				
20074	10240	flake	0				
20096	10152	flake and some spheres	0				
20096	10183	a little broken flake	0				
20098	10111	a little broken flake	0				
20106	10122	very little hammerscale	0				
20107	10126	a little broken flake	0				
20107	10137	some broken flake	0				
20109	10210	some broken flake	0				
20109	10236	very little hammerscale	0				
20111		undiagnostic	198				
20112	10180	flake	0				
20112	10195	a little flake, some spheres	0				
20112	10195	very little hammerscale	0				
20112	10246	a little flake	0				
20118	10148	a little flake	0				
20129		undiagnostic	162				
20129		vitriified hearth lining	56				
20158		pot?	4				
20158		stone (ore?)	100				
20158		undiagnostic	228				
20282		smithing hearth bottom	350	125	75	40	
<b>Total examined</b>			<b>13642 g</b>				