K1730 Condition Report

Conservation Started: 01/07/2013 Conservation Finished: 01/07/2013 Conservator: Cymbeline Storey

Time Taken: 0.75 hour

Including digital photography, report, conservation and packing.

Dimensions: (L) 10mm (Diam) 5mm (head); (Diam) shanks 2.5mm

Weight before: 0.47g Weight after: 0.46g Catalogue number: 667

Digital photography:

Taken with a Keyence VHX-1000 3D digital microscope with LED and/or fibre optic lights (20-200x

magnification). Taken before and after.

X-ray: L100

Annotation on any of the storage bags or boxes: None

Description: Visual and microscopic examination using Meiji stereo microscope 7-75x magnification

Silver pin with domed head and straight, broken shaft.

Associated Objects: TBC

Pre-Conservation Condition: Visual and microscopic examination using Meiji stereo microscope 7-75x magnification

The shaft of the pin is broken off; the break edge looks old. There is a little soil, particularly underneath the head. Some green corrosion products cover the shaft and head. Visible silver surface is tarnished (probably from burial) to a mid-grey colour.

Treatment: Carried out using a Meiji stereo microscope

Purpose: Study
Aim: Total cleaning

Materials: Soft natural/synthetic brushes, thorn in pin vice/holder, IMS on metals, 50:50 water/IMS on

metals

The granular soil on the front/back was mechanically removed or reduced where possible using a fine thorn tip secured in a pin vice and a small pure bristle brush. IMS or water was used to soften the soil to facilitate removal. Loose particles of soil were then removed with a small swab of IMS.

Corrosion products were left in situ; corrosion was not active and can be further cleaned or stabilised at a later date.

A storage box padded with white polyethylene foam was made for housing the object.

Post-Conservation Condition/Findings:

The condition of the object is the same as pre-conservation apart from removal of a small amount of soil.

Key Features:

- Silver pin with domed head and straight, broken shaft
- Green corrosion products on surface

Samples:

None