



OASTRIVS

898K

EC2

London [watching brief on 2 dropschaffts Old Jewry / Cheapside
in London Archaeologist Winter 2015, Vol 14 no. 3

NOT SEEN p. 81 - 82, Michael Marshall & Amy Thorp. Vessel 3 only right fac. side survives. Hole through centre - fig. 5. Said to have no grit inside ~~footcheck central hole~~. Base described as very thick & poorly made. No grit on flange in photograph, why is hole there? The spont codes odd. Only counterstamp survives. Diam. 125 mm. I need to see the wear. If this is a spotted bowl, it should be checked for any wear. No ~~other~~ examples of this form from PTO

productum sitē (check). It should be drawn because it is only example) this shape.

OASTRIVS
No. 1 Poultry, London [Context 12686 Mus Acc. no. 4620 ONE 94 4467K] PTO

Stamped along LV (D.F. 100g. ?28) diam. 8% greyish-cream fabric with buff-cream slip. Abundant quartz, mod. well-sorted, tiny to small with rare orange-brown inclusions. Fragment surviving has smooth flange but only areas with stamp ^{closely packed} intruded right up to bottom of bead; flint with some qtz & rare opaque orange-brown. 1/2 of qtz quartz pinkish. PTO

No. 1 Poultry, London [Context 18204 Mus. Acc. no. 5738 ONE 94 467K] r. facing stamped along. 630g. Diam 27 mm. 29% stamp longer than for eg. 146 Verulamium - might be some difference between being stamped along or across the flange. Fabric as above. Flange smooth; intrusion up to b of bead; abundant small flint, some quartz, PTO

NB Both have smooth flange

stamp slightly sharper than same.

NB Form & way of gritting up both identical with LVG DV (small)
stamping along also.

rare red-brown. Grit worn away in lower half of vessel.

RP. 90

Ext

Highgate Wood [5K HW 7.0 T82 F1 N~~Ext~~ (3.0.7.70), R.R. 90] frag. IRS

Sandy (granular) pinkish fabric w/ thick grey core. Stamps
 eroded. Different vessel. Abundant inclusions mainly quartz
~~battered~~ [525].

Highgate Wood [6K HW 6.9 RP 210] T61 F1 L⑥ (on pot HW 6.9 210)
 abundant quartz (smallish); perhaps some flint walls
 L-facing. Granular cream fabric. abundant unknown grey +
 more v.-b. inclusions than often seen in Ver. reg.
 white flint; red-brown grit. Much grit on flange also -
 deliberately placed. Internal scoring inside but very little if any
 on flange. Dr 2.8 ^{but doesn't appear} possibly never used. A

London [Bellingsgate Lane Park in earth walled to Dartford. Mo18
 incomplete in section

Guy de la Bedoyère BAR Brit. Ser. 154 (1986) p. fig. no. 5A.
 r-facing. Intuition includes red-brown grit + flint + qtz. Intuition. Fabric assumed

H.W.
Belair
 $\text{y}_{T_0} \leq 160/170$
5 km

OASTRIVS. VATERVS. & ASTRIVS.

London* [CRS unregistered; British Mus. 5K] r. facing; scoring on flange and
much grit; flange is spent; slightly sandy, pink fabric with cream surface;
orangey buff near spent. Grit & scoring on flange.


London. [Royal Ontario Museum OA SRNS LV 510. F. Information Plaque]
Vernaculum [58 DTT ④ 2 / 1. 249K] flange fragment. Sandy,
greyish cream fabric with thick pink core; concentric scoring
on top of flange & much tiny grit, white, v/b, grey.

Colchester [4M5 7.24 . 576K] l. facing. A small mortarium
with overhanging rim, near B.F.50. Hole worn in bottom
plugged with lead. D = c. 8". Sandy, cream fabric with
thick pink core. Vernaculum Region. Counterstamp.

OASTRINS

Hunt House, Southwark [HH 097] 1032 sent by M Lyne 54K]

162g Dr. 32cm 8%. Whole surface & upto 1mm of fabric is discoloured to almost chocolate brown. The internal fabric is creamy-buff and packed with fairly well-sorted quartz inclusions. Few tituration grits but the grit on flange shows to be flint & quartz with rare orange-brown. Inside and on top of flange has also concentric scoring.



Q A I S T R I V S - X E V G D F

DAT 11

Richborough [ii, p. 95, 10(A); M.Y; 17K] stamped diagonally on flange

fragment; sandy, grey fabric with dark grey patches on surface;
scoring on surface of flange; small, grey, black, white (? flint)
grit on flange. Approx. B.F. 34.

^{B.F.C} hondon [1937.81. Guildhall M. 128K] r. facing; stamped along; the name;
sandy, greyish white fabric; ^{usual out of shape.} drab cream-buff slip; blackened
surface in past; medium to large, grey, v. b. black grit, prolific in
top 1½ in. b. b. but worn away below.

^{Plantation Ho.} ^{heavy deep flange Scoring to outside.} hondon [13.4.36; 17, 440 on inside G.H. 192K] sandy, dirty cream fabric, pinkish in pat.
of core; grit mostly worn away but few v. b. & grey; internal scoring on flange & grit there.
D=10%o; Type 95K M.R.T.N.F.C, but flange longer.

OASTRIVS

April 2007

ANCOL (code)

Ancaster [^{rubbing} ~~Southgate~~ H. Dalling - Time Team] Dig in 2001 IIK Portcullis set


to Wessex Unit] iLV C.D Fo. Not seen East Field, in Ancaster,
General Grid Ref SK 9843 Stamp across rim. nospat
very worn.

OASTRIVS / LVAD-F

or OARRIVS

Gorhambury, [GOR 76 881] 2621 [7]. 7k] L. facing

join on IRS. Stamped along, 2 counter stamps close together; incomplete. Pinkish-cream fabric with very thick pinkish core; moderate inclusions. Fairly ill-sorted quartz + red-brown fragments. Trituration grit flint, quartz and red-brown fragments (3-4 mm.); finer (1-2 mm) fragments over flange. Dr. c. 30 cm.



Colchester [Hospital 1908; 435K] sandy, pink fabric, creamier towards surfaces,
but surfaces burnt red-pink; stamp broken.

Venlanium [58 B.I. (b); 146K] flange + bead only; sandy; pink
core changing to buff, surface sl. orangy buff; much black, r/b,
grey, flint, medium to small grit on flange. 1 or 2 inside. D=1.2 $\frac{1}{2}$ " Δ

Venlanium [?60 A III (9); 197K] L-facing; sandy, orangish fabric;
top surface cream; much grey and brown, medium to small
grit + on flange; stamped along; brownish buff slip;
counterstamp.

Colchester [Woolacombe M. no. no.] v. facing; cream fabric with core
slip; sandy; flange + top fragment.



① ASTRIVS or OARRIVS

Veniamium [60.A-120/1-270K] flange & body fragment. Burnt grey whitish quartz-like grit; smallish. Some greyish-greenish brown accretion on flange top side; mixed flint grit on flange, probably below surface skin. Interstitial grit may be flint.

The Hunt, Baginton [LRF 69 TCW P. 7. 21K] flange. Sandy greyish cream fabric with dark grey core; cream slip; across flange Veniamium [76.1.9B/A] Insula XVIII from well-stratified deposit probably Neronian / Early Flavian. (C. Saunders V. Mar.) LVCID 3d4K! Flange fragment in greyish cream fabric with pink core. Grains lar. NOT drawatable fine quantity in fabric; abundant; occcl. ill-sorted v/b & black.

~~KARRI CARVENS~~ FLUGD OASTRINS FLUGD

Wantage, Wilts [3K V.Swan]. Two rim fragments probably from the same vessel. Sandy greyish cream fabric with thick brownish-pink core & brownish buff slip; concentric scoring on top of flange & grey & blackish grit on it.

Colchester [PSO 98 BKC K386 64^{KK} S15] York.
buff fabric; surface fairly smooth. Munsell 5 YR 7/6. Orange-brown slip. Inclusions: fairly frequent & frequent, tiny to small, ill-sorted, quartz. Flange fragment. Finger dent under flange.

OARRIVS || LVQDF

(Little Munden Farm)

Bricket Wood [TL 1380 14, Herts. Site no. 74.4], FC 2/4 + 3/4

IK. Vessel is virtually complete - hole top side + 1 in bottom where base has blown. Grit entirely unknown. Stamped

OARRIVS || LVQDF. Granular cream fabric with slightly darker surface. Probably self-coloured. Concentric scoring throughout inside + a flange combined with heavy gritting inside + on flange. The grit may be medium-sized + very varied certainly includes flint, white + transparent quartz-like + red-brown grit. Dr. = 33.5 cms.

do. 744. FBI. LVQDF: twice near together. 2K
L. facing.

FBI 2 K Stamp impressed after scoring & cutting of
flange.

IK. Extra clay to spot certainly put on after scoring
& cutting off flange. *

All stamps impressed after scoring & cut.

Probably stamped all of his mortaria.

OAGRIVS ||LVGDF

Countertop ps only

Bricket Wood: F4.4 FC 1/4] D.F; (3)

74.4 FC 1/4 + 4/4 flange frag i] F o; (4)

74.4 FC 1/4 + 4/4 i LVGDF. F. o. (5)

74.4 FC 2/3 o LVGDF i. Fabre brune (6)K

slightly & faint cracking on flange.

74.4 FC 2/4 + 4/4 o LVGDF [i trace close together 7K

74.4 FC 1/4 + 4/4 flange flake LVGDF [Dk which way 8K

OARRINS

Namestamps

FD

Bricketwood	74 . 4 FC	4/4	? i]	VS	o? flake	9K
" "	74 . 4 FC	3/4 + 4/4] A RR [flake		10K
" "	74 . 4 FC	1/4 + 4/4	o A R R I N [flake		11K
" "	74 . 4 FB 1 o]	vs i	flake	trinadose nq.		12K
" "	74 . 4 FC	4/4 o]	vs i	flake	r. facig.	13K
stamped twice close together						

FD = stake hole

FC = Kiln

FB = Gully

CA = Ditch

Edges of stamps. 74-4 F.C. $\frac{3}{4}$ flake

" " " $\frac{4}{4}$ " ~tac.

" " F-D 2 flake ~tac

" " $\frac{4}{4} + \frac{4}{4}$ "

OCAICO

Brough-on-Humber [Corder, P. + Romans T., Excavations at the Roman Town at
Brough-Petervia 1937, Fig. 15 no. 23] No. 23 on pickle; IK Hull Museum;
published, laterally reversed; stamped each side of spout; Hand, orange
-brown fabric with grey core and cream slip; 1 red-brown grit and
var 2 translucent, colourless grit; D = 12". Δ - S. unstratified

M. O. GREICUS

cf. GREICUS

MESSOR [1935]

Colchester (G. Mus. Rep. 1931, 25);

London (G.T. (b))

OLOSSVS F ?

Colchester [Mr. Pollexfen; now BM. c. vii 1334 no 36] Not seen.

LOCCIVS.

York (Museum).

Stanground, nr. Whittlesea; cream fabric; multicoloured grit.

Camelon [⑩ CAM 76 KC Site A [3n. 13k] r. facing. Soft, A
yellowish.

brownish cream (2.5YR 8/4) fabric, moderate inclusions quartz,
dark red-brown fragments are common and sparse white
feldspars? Trituration grit quartz and white feldspars.
& probably flint.

ORBISSA

Canterbury, Burgate St. [6/65
~~6802~~, 21K] yellowish buff, soft; cream slip; small,
grey, black grit, very little; some on rim; a little internal scoring.
stamp on one side of spout only. ORBISSA PE Medicis No. 3. p. 17

Richborough [IV p. 250, no. 28; M25, 69K] L-facing. unstratified.
cream fabric; nearest B.F. 18 but turned down more. △

London [R. x 1.646 Guildhall M. 13K] L-facing; drab cream fabric; smooth;
very cleanly cut letters; △



/

ORBISSA

CONTINENTAL SITES.

Beauvais [CIL XIII, 10006, 64; St. Germaine 26294]

Boulogne [CIL XIII, 10006, 64]


Entraux 6K

ORGIL

Lincoln [East Right 356] ¹⁹⁶⁶ stamped along r. facing. Yellowish cream, fine-textured fabric. Clearly had been heavily grooved on the flange along with ^{little ironstone} flint + quartz-like grit; concentric grooving inside + much small + medium flint (grey-white) + quartz-like grits. D = 10° d.

Richborough [Site Mus. 115K] r. facing stamped along. Fine cream fabric; grit all over flange and on under layer beneath sport addition which has broken off; grit inside well worn, probably much worn away. Stamp worn + grit in stamp. Not published anywhere.

The Hunt, Baginton [LRF 69 M N 82K] l. facing. Fine-textured, yellowish cream fabric; much tiny grit (translucent; grey + white + dark + tan) on top of flange; stamped along.



→ opt

Lincoln (Ben Whetstone)

ORGIL

Greensforge, Kinner Staffs. U facing along. Surface badly cracked.

Fine textured cream fabric w/ brownish hue, looking much
brown on surface; some flint grit scattered on flange. I
think vessel stamped before grit added. Too near sp. &
decayed to show any ridging on flange.

Attributed: Bloomsberg Site 993K

OVID ^{uncertain.}
Oval pink fabric with dark grey zone; grit in it; white slip; white, grey, brown
grit.

Chester [Ring O' Bells Inn 1940; C.A.J. 36 p. 98; 10K]; exact parallel in stamp.

Warrington M. [405/13; 25K; possibly Wilderspool] soft, orange fabric with cream
slip; prolific, smallish to largish brown, grey grits to b.b. D = c. 13 ins.
l. facing; Type similar to

Warrington M. [48K; 302 '98] no prov., probably Wilderspool, l. facing,
certainly a different vessel.] orange fabric with creamy orange core & creamy
orange surface, cream slip; prolific, medium, red-brown, whitish
grits to top of head. D = c. 13 ins.

K8K Warrington M.
Lacing. 302:98.1.

OBVIOUS ?

? and the rollers


Venlamium [57. v xxxiii (10); 167K] r. facing; sandy, buff fabric with very

thick, grey core to very near surface; 1 r/b, + 2 dk grey + 1 white grits.


Venlamium [58. BTv (18J) 175K] stamped each side of spout; sandy,
brownish pink with grey core; good amount, large to smallish, black, brown, grey & tan grits
to c. 1" b.b.b; buff slip; D = 10%.

Sr. Albans [Venlam extra-mural. 153 S.R./AL 290K]. r. facing.

Sandy greyish cream fabric with thick pinkish core. Spout made
with ^{knif} scoop + fingers? Flint grit. Small hook.



175K *Venularia*
58.B.IV(185)



175K. *Venularia*
58.B.IV(185)

IV : 11 V : 1 XCV (OVID)

Check

Venitium [1558. BIV 123; 175K] stamped each side of spout; rather sandy,

pinkish buff fabric with grey core; much white, black, brown, and grey
medium and smallish grit to c. 1½ ins. b. b. b.; seems quite well worn. D = 10%

Venitium [57. Y VI A 6/14. 252K] stamped twice close
together, probably L-facing. Sandy, greyish cream fabric with
pink core; probably cream slip decolorized to grey in part.

Venitium [SP/AT/153 V-109 by]

OVIDVS

Venlawium region

Stantonbury, Milton Keynes, Bucks [with stamps] (125) 75 MK 301 .S1.①

F P(4) and 8 (29) 82 MK 301 (104) joining 52 75 MK 301 S1 (X);

[L. having.
9181 MK 301 301/40 2K] Flange fragments only. (52) has part of
shallow squat. Greyish-cream fabric with thick pink core; granular,
packed with inclusions: mostly whitish quartz; occasional r/brown &
probably some flint. To little survives to draw rim - flange frags only.

OVIDVS

Verceliorium region

(10)

Ashton [ASHT '82 (1013) +, (10). 10k] CRS, joining body sherd. Burnt
to gray throughout fabric, core slightly pinkish. Granular
fabric, frequent inclusions of quartz. Trituration grit
included flint and quartz, worn. Dr. 26 cm.
A

10k Ashton

(10) ASH '82

(1013) +

l.fac.