

Table 11. Results of compositional analysis, using CP-SEM-EDS, on three areas of the surface of the faience bead (Area 3 = ‘bright’ glaze area).

	<i>SiO₂</i>	<i>Al₂O₃</i>	<i>CaO</i>	<i>MgO</i>	<i>Na₂O</i>	<i>K₂O</i>	<i>Fe₂O₃</i>	<i>CuO</i>	<i>SnO₂</i>	<i>PbO</i>	<i>P₂O₅</i>	<i>SO₃</i>	<i>Cl</i>
Area 1	72.6	5.5	5.4	0.5	1.6	8.9	1.6	2.6	0.2	0.0	0.6	0.3	0.1
Area 2	72.0	5.5	5.4	0.6	2.0	9.0	1.8	2.7	0.0	0.0	0.6	0.2	0.1
Area 3	60.7	5.4	2.8	0.7	1.9	7.1	1.7	1.9	16.9	0.0	0.4	0.4	0.1